

Catalogue dimensions - PRECIZ® - precision-ground steel

We specialize in production and supplying of precision-ground tool and structural steel. The entire range of semi-finished products in lengths 500 and 1000 mm are being delivered directly from the production plant in Napajedla. That's why we are able to offer the maximum flexibility of supplies with dispatching time within 24 hours. **For e-shop orders you will get 5% discount. The transport within the Czech Republic is free of charge.**

The advantages of using machined semi-finished products:

- productivity growth
- growth of the production efficiency
- reducing production time
- shortening delivery dates
- increasing of the production flexibility
- decarbonization layer removal
- optimal hardening allowance
- inventory decrease
- demanded purchase
- eliminating preparatory operations
- elimination of material roughing
- lower number of employees needed
- machinery time capacity saving
- lower machinery depreciation
- less paperwork
- fast deliveries
- dispatch within 24 hours directly from the warehouse

We deliver most widely used steel:

- tool steel for cold forming
- tool steel for hot forming
- tool steel for plastic moulds production
- tool steel for press tools and jigs
- tool steel for injection moulds
- tool steel for guiding rails
- tool steel for industrial knives
- tool steel for forming tools
- structural steel for press tools and jigs
- structural steel for case-hardening and nitriding

Custom dimensions – semi-finished products, milled and grinded steel plates

If our catalogue offer doesn't suit your needs, we are offering production of customized, precision ground and angled semi-finished products based on your dimension and tolerances requirements.

Production of parts – guiding rails, industrial knives and plates

We produce precise flat parts including heat treatment (based on customer's drawing) for wide range of purposes in general engineering industry. The price quotation and delivery terms will be processed in accordance with your inquiry. **Upon your request, all parts can be measured on 3D measuring machine.**

Technological capabilities - PRECIZ®, s.r.o.

Vertical grinder

1000 x 350 x 7500 mm
650 x 200 x 8100 mm
350 x 200 x 6000 mm
400 x 300 x 4000 mm
600 x 250 x 5150 mm
tip. magnet 0-90°
350 x 200 x 3100 mm
accuracy of dimension 0,05 mm
parallelism 0,03 mm

Horizontal grinder

600 x 900 x 2100 mm
accuracy of dimension 0,005 mm
parallelism 0,005 mm

CNC vertical centre

MATEC 30HV – 800 x 800 x 3000 mm
MATEC 40L – 800 x 950 x 6000 mm
MATEC 50HV
1000 x 1100 x 4000 mm + Ø 1430 mm
DMG DMC100H – 1000 x 1000 x 1000 mm
AMADA THV800 – 800 x 230 x 800 mm

3D measurement

Wenzel LH65 – 600 x 500 x 4000 mm

Heat treatment

hardening in salt bath up to 3000 mm
induction hardening up to 4000 mm
nitriding, case hardening,
heat treatment, annealing

Services

Possibility to use our technologies for flat grinding – vertical and horizontal grinders, 3-5 axis CNC vertical centres.

Technical consulting service and support – if needed, we might assist you with technical documentation based on your requirements and material consultancy in terms of properties and usage.



PRECIZ, s.r.o.


A company of the PRÄZI GROUP



PRECIZ – precision-ground steel



Part production



Lime sand brick moulds



Screw worm conveyors



Feeding systems – biogas



Plates for moulds



We will gladly
make a quotation for you ...



PRECIZ®, s.r.o.

Kvítkovická 1627
763 61 Napajedla, Czech Republic
Phone: +420 577 113 040
Fax: +420 577 923 457
E-mail: sales@preciz.cz
E-shop: shop.preciz.cz



For cold work

W.Nr.	STOCK	DIN	ČSN	Böhler	Uddeholm	AISI	Poldi	AFNOR	PN	C	Si	Mn	≤ P	≤ S	Cr	Mo	Ni	V	W	Co	B	CE
1.0570	●	St52-3 (S355J2G3)	11 523			50		E 36	18G2A	≤ 0,2	≤ 0,55	≤ 1,60	0,035	0,035	-	-	-	-	-	-	-	-
1.1730	●	C 45W	19 083	K 945	UHB 11	SAE 1045	T6H EXTRA / W6H	XC 48	C 45	0,40-0,50	0,15-0,40	0,60-0,80	0,035	0,035	-	-	-	-	-	-	-	-
1.7225	●	42CrMo4	15 142	V 320		4140 / 4137	CM5	42CD4	40 HM	0,38-0,45	≤ 0,4	0,60-0,90	0,035	0,035	0,90-1,20	0,15-0,30	-	-	-	-	-	-
1.7131		16MnCr5	14 220	E 410SB		5120 / 5115	CE2	16MC5	16 HG	0,14-0,19	≤ 0,4	1,00-1,30	0,035	0,035	0,80-1,10	-	-	-	-	-	-	-
1.2162	●	21MnCr5	19 487	M 100		~ P2	CE4 SPECIAL	20 MC5	~ 20 HG	0,18-0,24	0,15-0,35	1,10-1,40	0,030	0,030	1,00-1,30	-	-	-	-	-	-	-
1.2842	●	90MnCrV8	19 313	K 720		O2	STABIL SP	90 MCV8	NMV	0,85-0,95	0,10-0,40	1,90-2,10	0,030	0,030	0,20-0,50	-	-	-	-	-	-	-
1.2510		100MnCrW4	19 314	K 460	Arne	O1	STABIL K	90 MWCV5	NMWW	0,90-1,05	0,15-0,35	1,00-1,20	0,035	0,035	0,50-0,70	-	-	0,05-0,15	-	-	-	-
1.2436	●	X210CrW12	19 437	K 107	Sverker 3	D6 / ~ D3	2002D	Z210CW12-01	~ NC 11	2,00-2,30	0,10-0,40	0,30-0,60	0,030	0,030	11,00-13,00	-	-	-	0,60-0,80	-	-	-
1.2080		X210Cr12	19 436	K 100		D3	2002	Z200C12	NC 11	1,90-2,20	0,10-0,60	0,20-0,60	0,030	0,030	11,00-13,00	-	-	-	-	-	-	-
1.2379	●	X153CrMoV12	19 573	K 110	Sverker 21	D2	2002K	Z160CDV12	NC11LV	1,45-1,60	0,10-0,60	0,20-0,60	0,030	0,030	11,00-13,00	0,70-1,00	-	0,70-1,00	-	-	-	-
1.2363	●	X100CrMoV5-1	19 571	K 305	Rigor	A2	RAZU	Z100CDV5	NCLV	0,90-1,05	0,20-0,40	0,40-0,70	0,035	0,035	4,80-5,50	0,90-1,20	-	0,10-0,30	-	-	-	-
1.2767	●	X45NiCrMo16	19 641/655	K 600		6F7	CNBD	45 NCD16	NPV	0,40-0,50	0,10-0,40	0,20-0,50	0,030	0,030	1,20-1,50	0,15-0,35	3,80-4,30	-	-	-	-	-
1.2327		86CrMoV7								0,83-0,90	0,15-0,35	0,30-0,45	0,030	0,030	1,60-1,90	0,20-0,35	-	0,05-0,15	-	-	-	-
1.2360		X48CrMoV8.1.1								0,45-0,50	0,70-0,90	0,35-0,45	0,020	0,005	7,30-7,80	1,30-1,50	-	1,30-1,50	-	-	-	-
1.2362		X63CrMoV5-1	19 569				RAZM			0,60-0,65	1,00-1,20	0,30-0,50	0,035	0,035	5,00-5,50	1,00-1,30	-	0,25-0,35	-	-	-	-
1.4112	●	X90CrMoV18	17 042							0,95	1	1	0,04	0,015	19	1,30	-	0,12	-	-	-	-
Toolox 33	●	1.2311/12 / 1.2738								0,25	0,60	0,90	0,010	0,004	1,20	0,40	0,70	0,125	-	-	0,002	0,48
Toolox 44	●	1.2342/1.2344								0,31	0,60	0,90	0,010	0,004	1,35	0,80	0,70	0,145	-	-	0,002	0,57

For hot work

W.Nr.	STOCK	DIN	ČSN	Böhler	Uddeholm	AISI	Poldi	AFNOR	PN	C	Si	Mn	≤ P	≤ S	Cr	Mo	Ni	V	W	Co	B	CE
1.2343	●	X38CrMoV 5-1	19 552	W 300	Vidar Supreme	H11	TLHG / TLH EFS	Z38CDV5	WCL	0,36-0,42	0,90-1,20	0,30-0,50	0,030	0,030	4,80-5,50	1,10-1,40	-	0,25-0,50	-	-	-	-
1.2343ESU	●	X37CrMoV 5-1	19 552							0,36-0,42	0,90-1,20	0,30-0,50	0,030	0,030	4,80-5,50	1,10-1,40	-	0,25-0,50	-	-	-	-
1.2367	●	X38CrMoV5-3		W 303			LNCR	Z38CDV5.3		0,35-0,40	0,30-0,50	0,30-0,60	0,035	0,035	4,70-5,20	2,70-3,30	-	0,40-0,70	-	-	-	-
1.2714		55NiCrMoV7	19 663	W 500	ALVAR 14	~ L6	TBM EXTRA 1	55NCD 07-05	~ WNL	0,50-0,60	0,10-0,40	0,65-0,95	0,030	0,030	0,80-1,20	0,35-0,55	1,50-1,80	0,05-0,15	-	-	-	-
1.2726		26NiCrMoV5								0,22-0,30	0,30-0,50	0,20-0,40	0,030	0,030	0,60-0,90	0,20-0,40	1,30-1,60	0,15-0,20	-	-	-	-
1.2740		28NiCrMoV10	19 675				TBM			0,24-0,32	0,30-0,50	0,20-0,40	0,030	0,030	0,60-0,90	0,50-0,70	2,30-2,60	0,25-0,32	-	-	-	-

For plastic moulds production

W.Nr.	STOCK	DIN	ČSN	Böhler	Uddeholm	AISI	Poldi	AFNOR	PN	C	Si	Mn	≤ P	≤ S	Cr	Mo	Ni	V	W	Co	B	CE
1.1730	●	C 45W	19 083	K 945	UHB 11	SAE 1045	T6H EXTRA / W6H	XC 48	C 45	0,40-0,50	0,15-0,40	0,60-0,80	0,035	0,035	-	-	-	-	-	-	-	-
1.2162	●	21MnCr5	19 487	M 100		~ P2	CE4 SPECIAL	20 MC5	~ 20 HG	0,18-0,24	0,15-0,35	1,10-1,40	0,030	0,030	1,00-1,30	-	-	-	-	-	-	-
1.2767	●	X45NiCrMo16	19 641 / 19 655	K 600		6F7	CNBD	45 NCD16	NPV	0,40-0,50	0,10-0,40	0,20-0,50	0,030	0,030	1,20-1,50	0,15-0,35	3,80-4,30	-	-	-	-	-
1.2311	●	40CrMnMo7	19 520	M 201		P 20	GS3D	~40 CMD		0,35-0,45	0,20-0,40	1,30-1,60	0,035	0,035	1,80-2,10	0,15-0,25	-	-	-	-	-	-
1.2312	●	40CrMnMoS8-6	19 520+S	M 200	Holdax	P 20+S	GS3S	~40 CMD8+S	~ 40 H	0,35-0,45	0,30-0,50	1,40-1,60	0,030	0,05-0,1	1,80-2,00	0,15-0,25	-	-	-	-	-	-
1.2085	●	X33CrS16		M 314		422+S		Z33CS16	~ 4H13+S	0,28-0,38	≤ 1	≤ 1	0,030	0,05-0,1	15,00-17,00	-	≤ 1	-	-	-	-	-
1.2343	●	X38CrMoV 5-1	19 552	W 300	Vidar Supreme	H11	TLHG / TLH EFS	Z38CDV5	WCL	0,36-0,42	0,90-1,20	0,30-0,50	0,030	0,030	4,80-5,50	1,10-1,40	-	0,25-0,50	-	-	-	-
1.2083	●	X42Cr13	~19 433	M 310	Polmax / Stavax	420	AK4R	Z40C14		0,38-0,45	≤ 1	≤ 1	0,030	0,030	12,50-13,50	-	-	-	-	-	-	-
1.2361		X91CrMoV18								0,86-0,96	≤ 1	≤ 1	0,045	0,030	17,00-19,00	0,90-1,30	≤ 0,30	0,07-0,12	-	-	Cu ≤ 0,30	-
1.2711		54NiCrMoV6		W 500		6F3		55 NCDV 7		0,50-0,60	0,15-0,35	0,50-0,80	0,025	0,025	0,60-0,80	0,25-0,35	1,50-1,80	0,07-0,12	-	-	-	-
Toolox 33	●	1.2311/12 / 1.2738								0,25	0,60	0,90	0,010	0,004	1,20	0,40	0,70	0,125	-	-	0,002	0,48
Toolox 44	●	1.2342 / 1.2344								0,31	0,60	0,90	0,010	0,004	1,35	0,80	0,70	0,145	-	-	0,002	0,57

High speed steel

W.Nr.	STOCK	DIN	ČSN	Böhler	Uddeholm	AISI	Poldi	AFNOR	PN	C	Si	Mn	≤ P	≤ S	Cr	Mo	Ni	V	W	Co	B	CE
1.3343	●	HS 6-5-2	19 830						SW7M	0,94	0,45	0,40	0,030	0,030		5,20		2,10	6,70			